




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G11B 7/26, 7/007	A1	(11) International Publication Number: WO 99/52105 (43) International Publication Date: 14 October 1999 (14.10.99)
(21) International Application Number: PCT/US99/07258 (22) International Filing Date: 2 April 1999 (02.04.99) (30) Priority Data: 09/055,825 6 April 1998 (06.04.98) US (71) Applicant: IMATION CORP. [US/US]; 1 Imation Place, P.O. Box 64898, Saint Paul, MN 55164-0898 (US). (72) Inventor: EDWARDS, Jathan, D.; P.O. Box 64898, Saint Paul, MN 55164-0898 (US). (74) Agents: LEVINSON, Eric, D. et al.; Imation Legal Affairs, P.O. Box 64898, Saint Paul, MN 55164-0898 (US).		(81) Designated States: CN, DE, GB, JP. Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: REVERSE OPTICAL MASTERING FOR DATA STORAGE DISKS



(57) Abstract

A data storage master disk and method of making a data storage master disk (20). The data storage disk master is for use in a data storage disk replication process. The data storage disk molding processes produces replica disks having a surface relief pattern with replica lands and replica grooves. The method includes providing a master substrate (32). The master substrate is at least partially covered with a layer of photosensitive material (30). A surface relief pattern having master lands (34) and master grooves (36) is recorded in the data storage disk master, including the steps of exposing and developing the photosensitive material. The exposing and developing of a specified thickness of photosensitive material is controlled to form master grooves extending down to a substrate interface between the master substrate and the layer of photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CJ	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroun	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

REVERSE OPTICAL MASTERING FOR DATA STORAGE DISKS

Technical Field

5 The present invention relates generally to the field of manufacture of optical data storage disks, and in particular, to an optical disk mastering process for use in a disk molding process, capable of molding data storage disks containing a high density of information.

Background of the Invention

10 Optical disks are produced by making a master which has a desired surface relief pattern formed therein. The surface relief pattern is created using an exposure step (e.g., by laser recording) and a subsequent development step. The master is used to make a stamper, which in turn is used to stamp out replicas in the form of optical master substrates. As such, the surface relief pattern, information and
15 precision of a single master can be transferred into many inexpensive replica optical disk substrates.

 During the mastering exposure step, the mastering system synchronizes the translation position of a finely focused optical spot with the rotation of the master substrate to describe a generally concentric or spiral pattern of a desired track spacing or "track pitch" on the disk. The generally spiral track forming the desired
20 surface relief pattern as a result of the mastering process can be defined by high regions termed "lands" and lower adjacent regions termed "grooves" and/or pits (i.e., interrupted grooves). The recording power and size/shape of the focused optical spot (spot size) as well as the photosensitive material parameters determine
25 the final geometry revealed in the master disk during the subsequent development step. Normal mastering practice uses high contrast positive photoresist for the photosensitive material.

 Conventional mastering typically utilizes laser light with wavelength, λ , in range of $350 \text{ nm} < \lambda < 460 \text{ nm}$ focused through an objective with a numerical
30 aperture (NA) of $0.75 \text{ nm} < \text{NA} < 0.90$ to give a theoretical gaussian spot size of:

$$\text{SS} = 0.57\lambda/\text{NA} \text{ (full width at half maximum intensity (FWHM))}.$$

Thus, a 350 nm laser light with NA = 0.9 gives a theoretical spot size of 0.22 μm (FWHM) as the practical limit for conventional optics.

After the master is recorded, it is flooded with developer solution to reveal the exposure pattern applied by the master recording system. The dissolution of the photoresist in the developer solution is in proportion to the optical exposure previously received in the recording process. The dissolution rate of the photoresist can be modeled for given exposure and development conditions (see Trefonus, P., Daniels, B., "New Principal For Imaging Enhancement In Single Layer Positive Photoresist", Proc. of SPIE vol. 771 p.194 (1987), see also Dill F. et al., "Characterization of Positive Photoresists" IEEE Transactions on Electronic Devices, vol. ED-22 p. 445 (1975).) Expressions explained in these referenced technical papers can be used to model the effects of exposures from several adjacent tracks recorded in the photoresist and subsequently developed. The photoresist dissolution in the developer solution is in proportion to the optical exposure previously received (positive type resist). More accurately, the dissolution rate (R) is given by the Trefonas model as

$$R \text{ [nm/sec]} = R_0 \times (1-M)^q + R_b$$

Where R_0 and R_b are the dissolution rates of the fully exposed and unexposed photoresist (respectively), q is a resist parameter related to the resist contrast and M is the fractional unconverted photoactive compound in the resist. Typical values for commercially available resists are $q = 3$, $10 < R_0 < 200 \text{ [nm/sec]}$ and $R_b = 0$ for normal developer concentrations. The M term is dependent in a point-wise fashion on how much exposure was received in the resist ($E(x,y,z)$) and the resist's parametric sensitivity "C" per the Dill convention:

$$M(x,y,z) = \exp \{-C \times E(x,y,z)\}.$$

Since optical disk mastering typically uses only 50-200 nm of photoresist thickness, the z -dependence of exposure can safely be ignored so that the above equations can be combined to give

$$R = R_0 (1 - \exp \{-CE(x,y)\})^q;$$

or, with the exposure profile explicitly circular gaussian we may simplify to

$$R = R_0 (1 - \exp \{-CkP \exp [-r^2/SS^2]\})^q;$$

Where r measures the radial distance from the center of the spot ($r^2 = x^2 + y^2$), P is the recording power and k is a normalization constant for the gaussian function. This dissolution rate, multiplied by the development time (t_d), gives the depth of photoresist lost from its initial coating thickness (T_0), so that the final resist thickness ($T(t)$) is given by $T(t_d) = T_0 - t_d R_0 (1 - \exp \{-CkP \exp [-r^2/SS^2]\})^q$; From this expression one can see how optical exposure (P), development (t_d , R_0) and photoresist thickness (T_0) determines final surface relief pattern.

In some aspects, these expose/development processes may be compared with conventional photography. In photography, either exposure or development may be controlled/adjusted as necessary to obtain desired final development pattern. In this sense, one may consider the expose/development level as one process variable which may alternatively be controlled by recording power, development time, developer concentration, etc.

In the mastering process, it is desirable to simultaneously obtain wide lands (for user recorded features) and grooves of suitable depth for adequate tracking signals (e.g., greater than 50 nm). Higher density data storage disks often require the storage of a greater amount of information within the same or smaller size of disk area, resulting in smaller track pitch (i.e., distance between tracks) design criteria.

Attempts have been made to meet these design criteria. In prior art Figures 1-3, surface relief patterns of exemplary master disks formed using conventional disk mastering techniques are illustrated using the above expressions to model the effects of exposures from several adjacent tracks recorded in the photoresist layer and then developed. These comparison assume (1) typical photoresist and developer parameters, (2) constant development time (=40sec.), (3) $SS = 0.23 \mu\text{m}$, (4) track pitch of $0.375 \mu\text{m}$ and initial photoresist thickness of 100 nm. As recording power (or alternatively, development time) is increased to obtain deeper grooves, the residual land width diminishes and lands become more rounded due to overlap exposure from adjacent tracks. Partially developed photosensitive material exhibits a granular roughness greater than that of the photosensitive material as

initially coated on the disk. Roughness of lands worsens with deepening of grooves, resulting in additional noise in data readback.

More problems occur when the track pitch approaches the finite size of the mastering spot size. For formats where the desired track pitch is much larger ($> 2x$) than the finite size of the mastering spot size (ss), the photosensitive material erosion of the lands is negligible and conventional mastering can provide wide lands with a > 50 nm groove depth. However, for formats where the track pitch is $< 2x$ larger than the spot size, conventional mastering requires a compromise of either land width, groove depth, or both (due to overlap exposure from adjacent tracks).

In Figure 4, exemplary embodiments of the mandatory link between land width and groove depth when using conventional mastering processes is illustrated. (Examples of $0.375\ \mu\text{m}$ and $0.425\ \mu\text{m}$ track pitch with $0.22\ \mu\text{m}$ recording spot size). As the groove depth increases, the land width decreases. The master surface relief pattern geometries (i.e., land width/groove depth) are constrained for given conditions of track pitch and mastering spot size. This means the designer may not independently specify the desired parameters for replica land width and replica groove depth.

A secondary problem for conventional mastering is that the land width precision is limited by mechanical track pitch precision (e.g., mechanical precision of master recording system), which is increasingly difficult to control as track pitch decreases.

Summary of the Invention

The present invention provides a data storage master disk and method of making a data storage master disk wherein the user may independently specify the parameters of replica land width and replica groove depth. The data storage master disk is for use in a data storage disk molding process for producing replica disks which are capable of storing a high capacity of information using a variety of disk formats.

In a first embodiment, the present invention provides a method of making a data storage master disk for use in a data storage disk molding process. The data

storage disk molding process produces replica disks having a surface relief pattern with replica lands and replica grooves. The method includes the step of providing a master substrate. The master substrate is covered with a layer of photosensitive material having a specified thickness. A surface relief pattern having master lands and master grooves is recorded in the data storage master disk, including the steps of exposing and developing the photosensitive material. The exposing and developing of a specified thickness of a photosensitive material is controlled to form master grooves extending down to a substrate interface between the master substrate and the layer of photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands.

The thickness of the photosensitive material is specified and controlled to correspond to a desired depth of the replica grooves. In another aspect, the thickness of the photosensitive material is specified and controlled in dependence on master recording system spot size, desired track pitch, and desired depth of replica grooves. The step of controlling the exposure and development of the data storage master disk may include the step of controlling the exposing and developing of the photosensitive material to obtain a flat master groove bottom. In another aspect, the step of controlling the exposure and development of the data storage master disk includes the step of controlling the exposing and developing of the photosensitive material to obtain a smooth, flat master groove bottom, with smoothness determined by the master substrate.

The step of controlling the exposing and developing of the photosensitive material may include the step of controlling optical energy for exposing the photosensitive material to a degree sufficient to obtain a desired master groove bottom width after development and removal of the photosensitive material. In another aspect, the step of controlling the exposing and developing of the photosensitive material may include the step of controlling the development of the photosensitive material to a degree sufficient to obtain a desired master groove width after development and removal of the exposed photosensitive material.

The step of exposing and developing the data storage master disk may include the step of forming a groove bottom, wherein the groove bottom is flat relative to the master land. The step of exposing and developing the data storage master disk results in the data storage master disk having a master surface relief pattern defined by the master lands and the master grooves, wherein the surface relief pattern of the replica disks has an orientation which is inverse the orientation of the data storage master disk surface relief pattern.

The present invention may further provide the step of polishing the master substrate optically smooth; and forming a smooth master groove bottom using the master substrate. In one aspect, the step of providing a master substrate includes forming a master substrate made of glass. Preferably, the glass is polished. The photosensitive material may be bonded to the master substrate with or without intermediate layers.

The present invention may further provide for forming a first stamper using the data storage master disk. Replica disks are made using the first stamper. The step of making replica disks using the data storage master disk may be accomplished using a multiple generation stamper process.

In another embodiment, the present invention provides a method of making a replica disk from a master disk using an inverse stamping process. The replica disk is capable of storing high volumes of information. The replica disk includes a surface relief pattern with replica lands and replica grooves. The method includes the step of providing a master substrate. At least a portion of the master substrate is coated with a layer of photosensitive material to form the master disk. A surface relief pattern having master lands and master grooves is recorded in the master disk, including the steps of using a laser beam recorder for exposing the photosensitive material in a desired track pattern having a track pitch, and developing the photosensitive material. The exposing and developing of the photosensitive material is controlled for forming master grooves extending down to a substrate interface between the master substrate and the photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands. A first stamper is formed from the master disk. A

second stamper is formed from the first stamper. A replica disk is formed from the second stamper, the replica disk including a surface relief pattern having an orientation which is the inverse of the master disk.

5 The present invention may further provide the step of controlling the thickness of the layer of the photosensitive material to correspond to a desired depth of the replica grooves. The specified and controlled thickness of the photosensitive material depends on master recording system spot size, desired track pitch, and desired depth of replica grooves.

10 The step of controlling the exposing and developing of the photosensitive material may include the step of controlling the exposing and developing of the photosensitive material to obtain a flat master groove bottom. Recording a desired track pitch in the photosensitive material may further include the use of a focused laser beam at a spot size which is greater than one half of the track pitch.

15 The step of a master substrate may include providing a master substrate made of glass. Further, the master substrate may be polished.

In one aspect, the desired track pattern is a spiral track defined by adjacent master lands and master grooves, wherein the steps of exposing/developing the master disks includes forming a wide, flat master groove bottom defined by the disk substrate. The step of recording the master disk includes forming master groove
20 bottoms having a width which does not necessarily depend on the depth of the master groove for a desired track pitch. The resulting depth of the master groove is dependent on the specified thickness of the photosensitive material and the cumulative optical exposure received by the photosensitive layer at a position half way between two adjacent tracks. In particular, this depends on the desired groove
25 bottom width and the ratio of master recording spot size to desired track pitch.

In another embodiment, the present invention provides a master disk. The master disk includes a master substrate. A layer of photosensitive material covers at least a portion of the master substrate. The photosensitive material includes a surface relief pattern in the form of a track pattern defined by adjacent master lands
30 and master grooves. The master grooves extend down to the disk substrate, master

grooves including a master groove bottom and the master lands including a master land top, wherein the master groove bottom is wider than the master land top.

The master groove bottom is generally flat. In particular, the master groove bottom is flat relative to the master land top, and in particular, the master groove bottoms may be wide and flat relative to the master land tops. Preferably, the master groove bottoms include sharp corners. Additionally, all of the master groove bottoms on the exposed/developed master disk are level with each other to the precision of the master substrate flatness. This is important in flying head media applications, such as near field recording techniques, where small lenses fly in proximity to the replica disk surface.

The master grooves may include a groove depth which is proximate the thickness of the photosensitive material for cases where the track pitch is greater than approximately 1.6 times the spot size. In one aspect, the master grooves include a groove depth which is greater than 50 nm, track pitch is less than two times the mastering system spot size, and the width of the master groove bottom is greater than 25 percent of desired track pitch. In another aspect, the width of the master groove bottom is greater than 50 percent desired track pitch.

In another embodiment, the present invention provides a disk including a replica substrate having a first major surface and a second surface. The first major surface includes a surface relief pattern in the form of a track pattern defined by adjacent lands and grooves. The track pattern having a track pitch less than 425 nm, wherein the grooves extend down into the disk substrate. The grooves include a groove bottom and the replica lands include a land top, wherein the land top is flat. This is particularly important in near field recording techniques, wherein lens-to-media-surface separation is extremely critical.

In one aspect, the land top has a width greater than 25 percent of track pitch. In one preferred aspect for the track pitch less than or equal to 400 nm, the groove depth is greater than 80 nm and the land width is greater than 160 nm. Preferably, the land top is smooth and has sharp edges. In one preferred embodiment, the land tops are level with each other to the precision of the flatness of the master disk substrate. The land tops are level and at the same elevation

relative to the second major surface. This is important in flying head media applications, such as near field recording techniques, where small lenses fly in proximity to the replica disk surface.

5

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings are included to provide a further understanding of the present invention and are incorporated in and constitute a part of this specification. The drawings illustrate the embodiments of the present invention and together with the description serve to explain the principals of the invention. Other
10 embodiments of the present invention and many of the intended advantages of the present invention will be readily appreciated as the same become better understood by reference to the following detailed description when considered in connection with the accompanying drawings, in which like reference numerals designate like parts throughout the figures thereof, and wherein:

15

FIG. 1 is a partial cross section illustrating the surface relief pattern of a prior art recorded master disk;

FIG. 2 is a partial cross-section illustrating the surface relief pattern of another master disk made using a prior art recording process;

20

FIG. 3 is a partial cross-section illustrating the surface relief pattern of another master disk made using a prior art recording process;

FIG. 4 is a graph illustrating master groove depth versus master land width for a master disk using prior art mastering/recording techniques;

25

FIG. 5 is a plan view illustrating one exemplary embodiment of a recorded master disk made using a data storage disk mastering process in accordance with the present invention;

FIG. 6 is an enlarged partial cross-sectional view taken along line 6-6 of FIG. 5;

FIG. 7 is an enlarged partial cross-sectional view illustrating a step in making a master disk in accordance with the present invention;

30

FIG. 8 is a diagram illustrating another step in making a master disk in accordance with the present invention;

FIG. 9 is a diagram illustrating one exemplary embodiment of the surface geometry of a master disk made using the process in accordance with the present invention;

FIG. 10 is a diagram illustrating another exemplary embodiment of the surface geometry of a master disk made using the process in accordance with the present invention;

FIG. 11 is a diagram illustrating another exemplary embodiment of the surface geometry of a master disk made using the process in accordance with the present invention;

FIG. 12 is a graph illustrating maximal master groove depth versus master groove bottom width for examples of master disks made using the mastering process in accordance with the present invention;

FIG. 13-18 illustrate experimental atomic force microscope traces of several differing surface relief geometries for master disks recorded at 0.375 and 0.425 μm track pitch using the mastering process in accordance with the present invention;

FIG. 19 is a diagram illustrating groove orientation for replica disks made from a master disk in accordance with the present invention, using a multiple generation disk molding/replication process;

FIG. 20 is a block diagram illustrating a data storage disk mastering process in accordance with the present invention; and

FIG. 21 is a block diagram illustrating a process for making a replica disk using a master disk in accordance with the present invention.

DETAILED DESCRIPTION

The present invention includes a data storage master disk and optical disk mastering process for making the unique data storage master disk. The process in accordance with the present invention provides for a master data storage disk having grooves which extend down to the master substrate, resulting in deep, flat, and wide master disk grooves. The master disk can be used in a disk molding process which includes a reverse mastering/inverse stamping process, resulting in replica disks having wide, flat lands with sharp edges, and deep grooves relative to

replica disks formed using conventional mastering processes. As such, the present invention is particularly useful in enabling flexible design of surface relief geometry for molded data storage disks containing a high density of information. This includes the ability to create wide, flat land features even in replica disks having a track pitch of less than two times the mastering system laser beam spot size.

In FIG. 5, a data storage master disk 20 in accordance with the present invention is generally shown. Master disk 20 may be used as part of a disk replication process (e.g., a disk molding process) for producing various formats of optical data disks. The data features on the optical data disks may include data pits, grooves, bumps or ridges, and land or land areas. This includes current formats of audio CD, CD-ROM, and video disk, such as DVD, as well as future formats which use data features described herein. The definition of optical data disks may include various types of recordable optical disks (e.g., CDR, magneto-optic, or phase-change disk formats, which commonly use features, such as grooves or pits, for tracking and address identification, even though data is subsequently recorded by users.

Master disk 20 includes a surface relief pattern (i.e., surface geometry) in the form of "data tracks" 22 (shown enlarged for clarity) which may include features representing data encoded therein or which allow the storage, reading, and tracking of data thereon. Data tracks 22 on the optical disk can be arranged in a spiral track 24 originating at the disk center 26 and ending at the disk outer edge 28, or alternatively, the spiral track 24 may originate at the disk outer edge 28 and end at the disk center 26. The data can also lie in a series of concentric tracks spaced radially from the disk center 26. Master disk 20 may or may not include a center hole, and may be hubbed or hubless.

In FIG. 6, a partial cross-sectional view illustrating one exemplary embodiment of master disk 20 in accordance with the present invention is shown. Master disk 20 includes a data layer 30 and master substrate 32 (a portion of which is shown). The data layer 30 includes a surface relief pattern shown as data tracks 22. The data tracks 22 are defined by a series of adjacent master lands 34 and master grooves 36 formed in the data layer 30 (e.g., which form spiral track 24).

The master groove sides 38, 40 are defined by adjacent master lands 34, and include a master groove bottom 42 which is defined by the master substrate 32. Master substrate 32 provides for a wide, flat and smooth master groove bottom 42.

5 Data layer 30 is made of a photosensitive material, and more preferably, is made of a photopolymer or photoresist. Master grooves 36 have a depth 44 which is equal to the height of master lands 34 relative to master substrate 32, and related to the initial thickness of data layer 30. Master groove depth 44 may further be dependent on mastering spot size, track pitch, and photoresist contrast. Preferably, master grooves 36 have a depth greater than 50 nm, and which typically ranges
10 between 50 nm and 120 nm. Master groove bottom 42 is preferably flat and smooth as defined by master substrate 32, having a width 46 which is preferably greater than 35 percent of the desired track pitch.

In one preferred embodiment, master substrate 32 is made of glass, and is preferably polished and/or optically smooth. The master substrate 32 typically
15 varies in thickness between 5 mm and 6 mm. Data layer 30 can be bonded to master substrate 32. In particular, data layer 30 may be coated directly to master substrate 32 or may include an intermediate layer (which may be a bonding layer).

The disk mastering process in accordance with the present invention provides for master disk 20 having relatively deep master grooves 36 with wide, flat
20 master groove bottoms 42. As such, when master disk 20 is used in a reverse optical disk mastering process, the master lands and master grooves translate into a replica disk having relatively deep grooves and wide flat lands. Such characteristics are preferred for many high density and writeable optical disk formats.

The master groove bottoms defined by the disk mastering process in
25 accordance with the present invention are flat (as opposed to rounded in the conventional process) with smoothness defined by the master substrate (e.g., polished glass) and includes sharp corners. When used in connection with an inverse stamping process, this corresponds to replica disks having wide, flat smooth lands with sharp corners, and deep grooves. Wide, flat lands are advantageous for
30 positioning user recorded data thereon. The sharp corners provide domain confinement for user recorded data (e.g., applications wherein data is magneto-

optically recorded on the tops of lands). The wide, flat lands with sharp corners and deep grooves provide for improved tracking or trackability of the media substrate. The replica disk land tops are very smooth, due to the groove bottoms 42 which are defined by the master substrate 32, which is preferably optically polished glass. The smoothness of the land tops is defined by the substrate interface between the master substrate 32 and the layer of photosensitive material 30. Smoothness of land tops results in a reduction of noise in subsequent readout of data from the disk.

Further, the wide, flat lands are level with each other, due to the groove bottoms 42 being defined by the master substrate 32. The flat lands are level with each other and at the same elevation, enhancing the flyability of the disk substrate for flying head applications.

Referring to FIG. 7 and 8, a method of making an optical disk master for use in a data storage disk molding process, in accordance with the present invention, is illustrated. In FIG. 7, master substrate 32 is provided which is preferably made of glass. Master substrate 32 typically ranges in thickness between 5 mm and 6 mm. Master substrate 32 includes major surface 50. Preferably, major surface 50 is polished optically smooth. Major surface 50 is at least partially covered (e.g., coated) by data layer 30. Data layer 30 may also be coated over an intermediate (e.g., bonding) layer 60 (not shown).

Referring to FIG. 8, master disk 20 is positioned on a master recording system (e.g., a laser recorder or a mask recording system). In one exemplary embodiment, the master recording system 60 includes controller 61, linear translation system 62, master recorder 64, and recording table 66. Master recording system 60 provides for controlled exposure of master disk 20 with a focused spot of laser light to encode the desired surface relief pattern (i.e., geometry) or data tracks therein.

Master disk 20 is placed on recording table 66, and can be registered (e.g., centered) about a center axis 68, relative to a master recorder 64 using techniques as known in the art, such as through the use of a spindle, or hubbed master disk 20. Recording table 66 is rotatable about the center axis 68, indicated by rotation arrow

70, for rotation of master disk 20 during the disk recording process. Master recorder 64 modulates and focuses a laser beam 72 for exposure of data layer 30 in a desired pattern. Further, master recorder 64 is mechanically coupled to linear translation system 62 which provides for axial movement of master recorder 64
5 relative to center axis 68, indicated by directional arrow 76.

Controller 61 is coupled to linear translation system 62 and master recorder 64 (indicated at 61A) and is coupled to recording table 66 (indicated at 61B). The controller 61 operates to synchronize the translation position of the finally focused laser beam 72 with the rotation 70 of master disk 20 to expose spiral track 24 in
10 data layer 30. Further, controller 61 may operate to modulate laser beam 72 to expose pit regions (interrupted grooves) in the header area of the disk. Controller 61 can be a microprocessor based programmable logic controller, a computer, a sequence of logic gates, or other device which may be capable of performing a sequence of logical operations.

15 In accordance with the present invention, controller 61 operates to control the optical energy of master recording system 60 for exposing the photosensitive material of master disk 20 to a degree sufficient to obtain a desired master groove bottom width after development and removal of the exposed photosensitive material. Controlling the optical energy can include controlling either the recording
20 power or controlling the recording speed for exposing the photosensitive material to a degree sufficient to obtain a desired master groove bottom width after development and removal of the exposed photosensitive material. For example, controller 61 may operate to increase the recording power or decrease the recording speed, thereby increasing optical exposure of the photosensitive material.

25 The laser recorded master disk 20 is removed from the recording table 66 and flooded with a developer solution to reveal the exposure pattern provided by the master recording system 60. The amount of dissolution of the data layer 30 in the developer solution is in proportion to the optical energy previously received during the recording process. Further, the amount of dissolution of the data layer
30 30 in the developer solution is in proportion to development process parameters, including the concentration of the development solution, the development time and

temperature. The type of development solution can be similar to development solutions used in conventional recording processes as known to those skilled in the art. As such, by controlling the exposure and development processes, the desired surface relief pattern in the photosensitive material can be achieved. Since the master recording system 60 was controlled to fully dissolve portions of the data layer 30 down to the master substrate 32, the resulting master grooves (previously shown in FIG. 6) include master groove bottoms which are defined by the master substrate 32 and, in particular, for recorded track pitches of less than 2 times the mastering spot size. The above master disk process results in master lands having rounded peaks and master grooves having flat, wide and preferably smooth master groove bottoms.

In FIGS 9-11, exemplary embodiments are shown illustrating the surface relief pattern or data tracks for master disks 20A, 20B, 20C which have been "overexposed" or "overdeveloped" using the master recording process in accordance with the present invention. With each figure (i.e., FIG. 9-11), the amount of exposure/development of data layer 30 has been increased. Referring to FIG. 9, the master recording/developing process resulted in master lands 34A defining master grooves 36A exposed down to master substrate 32A. Master grooves 36A have a groove depth of 92 nm with a corresponding flat master groove bottom 42 having a width of 120 nm. Similarly, FIG. 10 illustrates surface relief pattern or data tracks 22B having master lands 34B which define master grooves 36B down to master substrate 32B. The master grooves 36B have a groove depth of 88 nm and a corresponding flat master groove bottom 42 which is 160 nm wide. FIG. 11 illustrates master disk 20C having master lands 34C which define master grooves 36C having master groove bottom 42C defined by master substrate 32C. Master groove 36C has a groove depth of 82 nm and a flat master groove bottom 42 which is 200 nm wide. The more master disk 20 is overexposed during disk recording process, the greater the erosion of the master lands and wider master groove bottoms are achieved.

In FIG. 12, a graph illustrating the corresponding relationship between master land width and master groove depth using the master recording process in

accordance with the present invention is shown. Using conventional mastering processes, for a given data layer thickness, master groove depth and master groove bottom width are linked and dependent upon each other (see FIG. 4). Using the mastering process in accordance with the present invention, by selection of the initial thickness of the data layer and expose/development level, one can independently specify land width and groove depth. In other words, master groove depth is not dependent upon master groove bottom width, and master groove bottom width is not dependent upon master groove depth. The two parameters are separable, and by selection a desired data layer thickness, and controlling exposure and development criteria, a desired design criteria for the master disk may be obtained.

In the exemplary embodiment shown, plots are shown illustrating design criteria achieved by increasing initial photosensitive (data) layer thickness (plot 78) and/or increasing exposure energy/development of the photosensitive layer (plot 79). In all examples, a 0.22 μm spot size is assumed. Plot 80 had an initial data layer thickness of 120 nm, plot 82 had an initial data layer thickness of 100 nm, plot 84 had an initial data layer thickness of 80 nm, and plot 86 had an initial data layer thickness of 60 nm. As illustrated, master surface geometries are no longer constrained by the master land width to master groove depth linkage as in conventional mastering processes. By starting with different initial data layer thicknesses and controlling expose/development level, any point within the width-depth parameter space may be obtained using the disk mastering process in accordance with the present invention. Whereas FIG. 12 shows how by starting with differing initial photosensitive material thickness that any point in the width-depth parameter space may be obtained, FIGS. 13-18 show corroborating experimental results illustrated by atomic force microscope (AFM) traces of several differing geometries at 0.375 and 0.425 μm track pitch using the disk mastering process in accordance with the present invention.

The master recording process in accordance with the present invention is (preferably) used in a reverse mastering or inverse stamping process, for creation of replica disks having wide, flat (and smooth) land features at track pitches less than

two times the mastering system spot size. In FIG. 19, a diagram illustrating "groove" orientation of an optical disk substrate (i.e., a replica disk) molded from a first generation stamper, a second generation stamper or a third generation stamper formed from a master disk in accordance with the present invention, is shown. The diagram includes enlarged, partial cross-sections illustrating the orientation of the data tracks of a master disk 90, first generation stamper 92, second generation stamper 94, third generation stamper 96, replica disk substrate 1, replica disk substrate 2, and replica disk substrate 3. Data tracks are recorded onto the master disk 90, and have an orientation based on whether a replica disk substrate is molded from a first, second or third generation stamper.

In particular, master disk 90 includes master data layer 104 having master lands 106 and master groove 108. First generation stamper 92 includes first generation stamper data layer 110 having first generation stamper lands 112 and first generation stamper grooves 114. Second generation stamper 94 includes second generation stamper data layer 116 having second generation stamper lands 118 and second generation stamper grooves 120. Third generation stamper 96 includes third generation stamper data layer 122 having third generation stamper lands 124 and third generation stamper pits 126. Similarly, replica disk substrate 1 includes substrate 1 data layer 128 having substrate 1 lands 130 and substrate 1 grooves 132; replica disk substrate 2 includes substrate 2 data layer 134 having substrate 2 lands 136 and substrate 2 grooves 138; and replica disk substrate 3 includes substrate 3 data layer 140 having substrate 3 lands 142 and substrate grooves 144.

The orientation of substrate 1, data layer 128 molded from first generation stamper 92 corresponds to the orientation of the master disk data layer 104. In particular, the first generation stamper data layer 110 is the inverse of the master disk layer 104. Similarly, replica disk substrate 1 data layer 128 is the inverse of the first generation stamper data layer 110.

Second generation stamper 94 data layer 116 is the inverse of the first generation stamper 92 data layer 110, resulting in replica disk substrate 2 data layer 134 being the inverse of second generation stamper 94 data layer 116 and master

disk data layer 104. Likewise, third generation stamper 96 data layer 122 is the inverse of the second generation stamper 94 data layer 116. Accordingly, disk substrate 3, data layer 140 is the inverse of the third generation stamper data layer 122, and corresponds or has the same orientation as the master disk data layer 104.

5 It is recognized that the desired orientation of the master disk data layer 104 is dependent on the desired orientation of the replica disk substrate for its intended use. For the example of high-density replica disks having track pitches less than two times the mastering system spot size (and air incident media), it is desirable to use a master disk form using the master disk recording process in accordance with
10 the present invention and a second generation stamper process, resulting in a replica disk having wide, flat, smooth lands and deep grooves. Alternatively, for disks read through the substrate, a master disk formed using the master disk recording process in accordance with the present invention may be used in a first generation stamper or third generation stamper process where it is desired to mold a replica disk having
15 flat pits or grooves.

 Alternatively, other stamper processes may be utilized. For example, in another exemplary embodiment an electroforming pyramiding family process is used. This process involves the electroforming of a "father" stamper or first generation stamper from a master disk formed using the process in accordance with
20 the present invention. The father stamper is cleaned, treated and returned to the nickel bath to plate a "mother" or second generation stamper. This process cycle can be repeated several times, resulting in multiple "mother" stampers or second generation stamper being made from a single father or first generation stamper. The same electroforming process may be repeated using the "mother" stamper to make
25 several "daughter" or third generation stampers from each mother.

 In FIG. 20, a block diagram illustrating a process for making a replica disk using a master disk made in accordance with the present invention is shown at 110. The master disk is for use in a data storage disk molding process. The data storage disk molding process produces replica disks having a surface relief pattern with
30 replica lands and replica grooves. In the exemplary embodiment shown, the process 110 begins with providing a master substrate (112). The master substrate is at least

partially covered with a photosensitive material, which is preferably made of photoresist (114). A surface relief pattern having master lands and master grooves is recorded in the data storage master disk, including the steps of exposing and developing the photosensitive material (116). The exposing and developing of a
5 specified thickness of photosensitive material is controlled to form master grooves extending down to substrate interface between the master substrate and the layer of photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands (118).

The master disk can now be used to make a replica disk in a disk molding
10 process. In particular, a stamper is made from the optical master disk (120). A replica disk is made from the stamper (122). The replica disk is capable of storing high volumes of information. In one application, this invention is particularly useful for recording track pitches that are less than 2 times the master recorder spot size.

In FIG. 21, a block diagram illustrating one exemplary embodiment of using
15 a master disk in accordance with the present invention in a multiple generation disk molding process is shown at 130. The master disk is fabricated (132) using the unique methods previously described herein. The methods include exposing and developing the data layer down to the master substrate. A first generation stamper is made from the master disk (134). A replica disk may be made from the first
20 generation stamper (136).

Alternatively, a second generation stamper is made from the first generation stamper (138). A replica disk is made from the second generation stamper (140). Further, a third generation stamper can be made from the second generation stamper (142). A replica disk can be made from the third generation stamper (144).

25 Photosensitive materials include photopolymers or photoresist, or other materials or material blends having similar photosensitive characteristics. One group of suitable photosensitive material includes standard position type high resolution photoresist commercially available from vendors Shipley, OCG, etc. Other suitable photosensitive materials may become apparent to those skilled in the
30 art after reviewing this disclosure.

Suitable photopolymers for use in forming layers, replication layers, or bonding layers discussed herein, include HDDA (4x6x) polyethylenically unsaturated monomer-hexanediol diacrylate; chemlink 102 (3x) monoethylenically unsaturated monomer-diethylene glycol monoethyl ether acrylate, elvacite 2043 (1x3x) organic polymer-polyethylmethacrylate, and irgacure 651 (.1x.2) latent radical initiator -2,2-diamethoxy-2-phenylacetophenone. Another suitable photopolymer includes HHA (hydantoin hexacrylate) 1x, HDDA (hexanediol diacrylate) 1x, and irgacure 651 (.1x.2) latent radical initiator-2,2-dimethoxy-2-phenylacetophenone. Other suitable photopolymers may become apparent to those skilled in the art after reviewing this disclosure.

What is claimed:

1. A method of making a data storage disk master for use in a data storage disk molding process, wherein the data storage disk molding process produces
5 replica disks having a surface relief pattern with replica lands and replica grooves, the method comprising the steps of:
 providing a master substrate;
 covering the master substrate with a layer of photosensitive material;
 recording a surface relief pattern having master lands and master grooves in
10 the data storage disk master, including the steps of exposing and developing the photosensitive material; and
 controlling the exposing and developing of the a specified thickness of photosensitive material to form master grooves extending down to a substrate interface between the master substrate and the layer of
15 photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands.
2. A method of making a replica disk from a disk master using an inverse
20 stamping, process, the replica disk being capable of storing high volumes of information, the replica disk including a surface relief pattern with replica lands and replica grooves, the method comprising the steps of:
 providing a master substrate;
 coating at least a portion of the master substrate with a layer of
25 photosensitive material to form the disk master;
 recording a surface relief pattern having master lands and master grooves in the master disk, including the steps of using a laser beam recorder for exposing the photosensitive material in a desired track pattern having a track pitch, and developing the photosensitive material;
30 controlling the exposing and developing of the photosensitive material for forming master grooves extending down to a substrate interface

between the master substrate and the photosensitive material, such that the width of the master grooves at the substrate interface corresponds to a desired width of the replica lands;

forming a first stamper from the disk master;

5 forming a second stamper from the first stamper; and

forming a replica disk from the second stamper, the replica disk including a surface relief pattern having an orientation which is the inverse of the disk master.

10 3. The method of claims 1 or 2, further comprising the step of controlling the thickness of the photosensitive material to correspond to a desired depth of the replica grooves.

4. The method of claims 1 or 2, further comprising the step of specifying and
15 controlling the thickness of the photosensitive material in dependence on master recording system spot size, desired track pitch, and desired depth of replica grooves.

5. The method of claims 1 or 2, wherein the step of controlling the exposure
20 and development of the photosensitive material includes the step of controlling the exposing and developing of the photosensitive material to obtain a smooth, flat master groove bottom, with smoothness determined by the master substrate.

6. The method of claims 1 or 2, wherein the step of controlling the exposing
25 and developing of the photosensitive material includes the step of controlling the development of the photosensitive material to a degree sufficient to obtain a desired master groove bottom width after development and removal of the exposed photosensitive material.

7. The method of claims 1 or 2, wherein the step of exposing and developing the photosensitive material includes the step of forming a groove bottom, wherein the groove bottom is flat relative to the master land.

5 8. The method of claims 1 or 2, further comprising the steps of:
polishing the master substrate optically smooth; and
forming a smooth master groove bottom using the master substrate.

9. The method of claim 2, wherein the laser beam recorder uses a focused laser
10 beam at a spot size, and recording the master disk includes recording a desired track pitch which is less than two times the focused laser beam spot size.

10. A master disk comprising:
a master substrate;
15 a layer of photosensitive material covering at least a portion of the substrate,
the photosensitive material including a surface relief pattern in the
form of a track pattern defined by adjacent lands and grooves,
wherein the grooves extend down to the substrate, the grooves
including a groove bottom and the lands including a land top,
20 wherein the groove bottom is wider than the land top.

11. A stamper comprising:
a stamper substrate having a first major surface and second major surface,
the first major surface including a surface relief pattern in the form of
25 a track pattern defined by adjacent lands and grooves, wherein the
grooves extend down into the substrate, the grooves including a
groove bottom and the lands including a land top, wherein the
groove bottom is wider than the land top.

30 12. The article of claims 10 or 11, wherein the groove bottoms are generally flat and level with each other.

13. The article of claims 11 or 12, wherein the groove bottoms are wide and flat relative to the land tops.

5 14. The article of claims 11 or 12, wherein the groove bottoms have sharp corners.

15. The article of claims 11 or 12, wherein the grooves include a groove depth which is approximately equal to the thickness of the photosensitive material.

10

16. The article of claims 11 or 12, wherein the grooves include a groove depth which is greater than 100 nm.

17. The article of claim 16, wherein the track pitch is less than 425 nm.

15

18. The article of claims 11 or 12, wherein the width of the master groove bottom is greater than 250 nm.

19. The article of claim 17, wherein the groove bottom has a width greater than
20 35% of the track pitch.

20. A disk made from the article of any of claims 10-19.

1/9




FIG. 1
PRIOR ART




FIG. 2
PRIOR ART




FIG. 3
PRIOR ART

2/9




FIG. 4




FIG. 5

3/9




FIG. 6




FIG. 7







FIG. 8

4/9



5/9




FIG. 12

6/9

0.425 EXAMPLES




FIG. 13

0.375 EXAMPLES




FIG. 16




FIG. 14




FIG. 17




FIG. 15




FIG. 18




FIG. 19

8/9




FIG. 20

9/9




FIG. 21

INTERNATIONAL SEARCH REPORT

Intern. at Application No

PCT/US 99/07258

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G11B7/26 G11B7/007

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G11B B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 014, no. 150 (P-1025), 22 March 1990 (1990-03-22) & JP 02 010536 A (FUJI PHOTO FILM CO LTD), 16 January 1990 (1990-01-16) abstract	1.2. 10-15,20
X	PATENT ABSTRACTS OF JAPAN vol. 096, no. 010, 31 October 1996 (1996-10-31) & JP 08 147768 A (NIPPON COLUMBIA CO LTD), 7 June 1996 (1996-06-07) abstract	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

5 August 1999

Date of mailing of the international search report

11/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bernas, Y

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/07258

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 02010536 A	16-01-1990	NONE	
JP 08147768 A	07-06-1996	NONE	
JP 06060441 A	04-03-1994	NONE	
JP 02244440 A	28-09-1990	NONE	
EP 0444367 A	04-09-1991	JP 2061837 A JP 2519985 B US 5484324 A	01-03-1990 31-07-1996 16-01-1996
US 4150398 A	17-04-1979	JP 51082601 A AT 380987 B AT 30276 A AU 500575 B AU 1035676 A CA 1066549 A DE 2601407 A FR 2298155 A GB 1506966 A NL 7600507 A,B. SE 417878 B SE 7600402 A	20-07-1976 11-08-1986 15-12-1985 24-05-1979 21-07-1977 20-11-1979 22-07-1976 13-08-1976 12-04-1978 20-07-1976 13-04-1981 08-10-1976

